

QUALIFICATION TEST REPORT
WH-13-48
CLIMATIC CHAMBER EVALUATION OF THE
AIRCRAFT DEICING FLUID

Arctica DG91 Concentrate
lot # 11

Produced at Tatarstan, Russia

for

ARCTON LTD.
P.O. Box 1079
GO 11, Nizhnekamsk
423570, Tatarstan, Russia

by

Diane Paradis
Marc Mario Tremblay



Laboratoire international
des matériaux antigivre

LIMA  **AMIL**

Anti-icing Materials
International Laboratory

July 2013

QUALIFICATION

This report presents the anti-icing endurance times pertaining to samples of the deicing fluid **ARCTON LTD. Arctica DG91 Concentrate lot # 11** produced at **Tatarstan, Russia**, evaluated diluted with hard water, in Water Spray Endurance Tests (WSET) and High Humidity Endurance Tests (HHET) as per the latest revisions of the AMS 1424K specification [1] and AS5901B standard [2]. The tests were performed using the set-up in the climatic chamber at the Anti-icing Materials International Laboratory (AMIL) which is located at the Université du Québec à Chicoutimi (UQAC). AMIL is independent from fluid manufacturers. Fluids were at room temperature when they were applied to the plates. Fluid samples were sheared within two hours of the beginning of the test.

The required minimum anti-icing endurance time in WSET for a Type I fluid, concentrate or diluted, is 3 minutes. The required minimum anti-icing endurance time in HHET for a Type I fluid, concentrate or diluted, is 20 minutes.

The candidate fluid ARCTON LTD., Arctica DG91 Concentrate lot # 11 anti-icing endurance time averages are as follows:

1. **Arctica DG91 Concentrate, lot # 11, 75/25 dilution**
 - 4 min 44 s $\pm$ 16 s for WSET,
 - 29 min 18 s $\pm$ 1 min 59 s for HHET.
2. **Arctica DG91 Concentrate, lot # 11, 50/50 dilution**
 - 3 min 14 s $\pm$ 14 s for WSET,
 - 23 min 20 s $\pm$ 2 min 08 s for HHET.

On the basis of the test data, the fluid **ARCTON LTD., Arctica DG91 Concentrate lot # 11**, demonstrates acceptable anti-icing endurance time properties as required per SAE AMS 1424K specification with respect to a Type I fluid.

This fluid is qualified from 2013 July 29, for a four year period.



This page left blank.

TABLE OF CONTENTS

QUALIFICATION	i
LIST OF TABLES	iv
LIST OF FIGURES	iv
LIST OF SYMBOLS	v
TEST RESULTS.....	1
TEST DESCRIPTION	13
1. INTRODUCTION	15
2. TEST DESCRIPTION	15
2.1 Water Spray Endurance Test	15
2.2 High Humidity Endurance Test	19
2.3 Measurements	19
2.4 Calibration.....	21
3. TEST RESULTS.....	22
3.1 Test Presentation	22
3.2 Calibration.....	22
3.3 Water Spray Endurance Test	23
3.4 High Humidity Endurance Test	23
4. REFERENCES	24
ATTACHMENT	25

LIST OF TABLES

Table 1 - Fluid Identification	3
Table 2 - Climatic Chamber Test Identification	5
Table 3 - Water Spray Endurance Tests	7
Table 4 - High Humidity Endurance Tests	9
Table 5 - Brookfield Viscosity (mPa·s)	11
Table 6 - Required Experimental Test Parameters	17
Table 7 - Viscosity Measurement Details	22
Table 8 - Calibration Test Results	23

LIST OF FIGURES

Figure 1 - WSET Experimental Set-up	16
Figure 2 - Test Plate Failure Zone	16
Figure 3 - Droplet Diameter Distribution in WSET	18
Figure 4 - HHET Experimental Set-up	20
Figure 5 - Small Plate Position on Support.....	21

LIST OF SYMBOLS

σ	Standard Deviation
AMIL	Anti-icing Materials International Laboratory
AMS	Aerospace Material Specification
AS	Aerospace Standard
FIE	First Ice Event: period of elapsed time for first ice crystal to reach the 25 mm line (minutes and seconds)
HHET	High Humidity Endurance Test
I	Icing Intensity ($\text{g}/\text{dm}^2/\text{h}$)
I_{av}	Average Icing Intensity ($\text{g}/\text{dm}^2/\text{h}$)
MIT	Mean Icing Time: period of elapsed time to have a mean ice front at the 25 mm line (minutes and seconds)
n.a.	Not applicable
n.m.	Not measured
P_a	Air pressure of the spraying nozzle (kPa)
P_w	Water pressure of the spraying nozzle (kPa)
Rh	Relative humidity (%)
SAE	Society of Automotive Engineers
T_a	Temperature of the cold room ($^{\circ}\text{C}$)
T_p	Temperature of the plates on the refrigerated units ($^{\circ}\text{C}$)
UQAC	University of Quebec at Chicoutimi
WFR	Water Flow Rate from the nozzle (ml/min)
WSET	Water Spray Endurance Test

This page left blank.

TEST RESULTS

This page left blank

Table 1 - Fluid Identification

Company Name	Product	Color	Manufacture Location	Manuf. Date	AMIL Label	Recep. Date
ARCTON LTD.	Arctica DG91 Concentrate lot # 11 NEAT	Orange	Tatarstan, Russia	March 2013	J159	13-06-10
ARCTON LTD.	Arctica DG91 Concentrate lot # 11 75/25	Orange	Tatarstan, Russia	March 2013	J160	13-06-10
ARCTON LTD.	Arctica DG91 Concentrate lot # 11 50/50	Orange	Tatarstan, Russia	March 2013	J161	13-06-10

This page left blank

Table 2 - Climatic Chamber Test Identification

NUMBER	DATE	FLUID
WSC-2955	13-01-10	Calibration 30 minutes
CAHH-335	13-06-04	Calibration 120 minutes
WS-6732	13-07-11	75/25 Dilution
WS-6733	13-07-12	75/25 Dilution
WS-6730	13-07-10	50/50 Dilution
WS-6728	13-07-09	50/50 Dilution
HH-3003	13-07-26	75/25 Dilution
HH-2988	13-07-12	75/25 Dilution
HH-2983	13-07-05	50/50 Dilution
HH-2972	13-06-17	50/50 Dilution

This page left blank

Table 3 - Water Spray Endurance Tests

DEICING FLUID ARCTON LTD.
Arctica DG91 Concentrate, lot # 11

75/25 DILUTION

FLUID LABEL	TEST CODE	DATE y-m-d	ICE DATA		FLUID DATA		
			Plate	Intensity g/dm ² /h	Plate	FIE ¹ min:s	MIT ² min:s
J160	WS6732	13-07-11	P1	4.97 ± 0.09	P2	5:10	6:10
			P3	4.97 ± 0.14	P4	4:30	6:00
			P5	4.95 ± 0.11	P6	4:40	6:20
J160	WS6733	13-07-12	P2	4.87 ± 0.04	P1	4:30	6:15
			P4	4.95 ± 0.08	P3	4:40	6:05
			P6	4.88 ± 0.07	P5	4:55	6:10

50/50 DILUTION

FLUID LABEL	TEST CODE	DATE y-m-d	ICE DATA		FLUID DATA		
			Plate	Intensity g/dm ² /h	Plate	FIE ¹ min:s	MIT ² min:s
J161	WS6730	13-07-10	P1	5.03 ± 0.06	P2	3:00	3:30
			P3	4.91 ± 0.06	P4	3:00	3:20
			P5	4.92 ± 0.11	P6	3:05	3:25
J161	WS6728	13-07-09	P2	4.90 ± 0.04	P1	3:20	3:40
			P4	4.91 ± 0.06	P3	3:30	3:55
			P6	4.89 ± 0.06	P5	3:30	4:00

¹ FIE: First Ice Event: time for the first ice crystal to reach 25 mm in length.

² MIT: Mean Icing Time: time for the ice to reach a mean length of 25 mm.

This page left blank

Table 4 - High Humidity Endurance Tests

**DEICING FLUID ARCTON LTD.
Arctica DG91 Concentrate, lot # 11**

75/25 DILUTION

FLUID LABEL	TEST CODE	DATE y-m-d	ICE DATA		FLUID DATA		
			Plate	Intensity g/dm ² /h	Plate	FIE ¹ min:s	MIT ² min:s
J160	HH3003	13-07-26	P1	0.32 ± 0.03	P2	26:45	28:00
			P3	0.30 ± 0.02	P4	30:40	32:30
			P5	0.31 ± 0.01	P6	31:20	33:45
J160	HH2988	13-07-12	P2	0.31 ± 0.00	P1	27:45	34:30
			P4	0.30 ± 0.01	P3	28:10	32:25
			P6	0.31 ± 0.03	P5	31:10	35:00

50/50 DILUTION

FLUID LABEL	TEST CODE	DATE y-m-d	ICE DATA		FLUID DATA		
			Plate	Intensity g/dm ² /h	Plate	FIE ¹ min:s	MIT ² min:s
J161	HH2983	13-07-05	P1	0.33 ± 0.02	P2	21:05	22:10
			P3	0.29 ± 0.01	P4	21:05	22:20
			P5	0.31 ± 0.02	P6	22:40	23:20
J161	HH2972	13-06-17	P2	0.30 ± 0.01	P1	23:40	25:30
			P4	0.27 ± 0.01	P3	25:20	27:30
			P6	0.28 ± 0.02	P5	26:10	28:10

¹ FIE: First Ice Event: time for the first ice crystal to reach 25 mm in length.

² MIT: Mean Icing Time: time for the ice to reach a mean length of 25 mm.

This page left blank

Table 5 - Brookfield Viscosity (mPa·s)

**DEICING FLUID ARCTON LTD.
Arctica DG91 Concentrate, lot # 11**

Fluid	Temp (°C)	0.3 RPM			6 RPM			30 RPM		
		Viscosity	Accuracy	Spindle #	Viscosity	Accuracy	Spindle #	Viscosity	Accuracy	Spindle #
J160 Sheared*	20	< 20	200	1	11	10	1	11.0	2	1
	20	< 20	200	1	10	10	1	10.6	2	1
J161 Sheared*	20	< 20	200	1	5	10	1	5.0	2	1
	20	< 20	200	1	5	10	1	5.0	2	1

**Dilutions prepared with standard hardwater (AMS 1424K paragraph 3.3.3.1).*

For additional viscosity details, see Table 7.

This page left blank

TEST DESCRIPTION

This page left blank.

1. INTRODUCTION

This report details the performance of fluid samples, identified in Table 1, when subjected to the Water Spray and High Humidity Endurance Tests, denoted respectively WSET and HHET hereafter. WSET and HHET procedures are in accordance with the latest revisions of the SAE Aerospace Material Specifications AMS 1424K [1] and Aerospace Standard AS5901B [2] while carried out in the cold chamber of the "Anti-Icing Materials International Laboratory" (AMIL) at the "Université du Québec à Chicoutimi" (UQAC) [3, 4].

2. TEST DESCRIPTION

2.1 Water Spray Endurance Test

This test is designed to simulate freezing fog exposure of an aircraft when the temperature is below 0°C. During a WSET, a 10 cm x 30 cm aluminum plate is coated with a film of a candidate fluid. The plate is positioned with a downward slope of 10° and cooled to -5°C. It is then subjected to supercooled droplets at a prescribed average icing intensity of 5.0 g/dm²/h ± 0.2 g/dm²/h. The WSET set-up used is shown in Figure 1. The water spray is generated by a nozzle centered on a support at a 130 cm height and oscillating at ± 30° at 3 cycles per minute. Required experimental parameters and specifications are detailed in Table 6 and the droplet diameter distribution is exhibited in Figure 3.




Figure 1 - WSET Experimental Set-up




Figure 2 - Test Plate Failure Zone

Table 6 - Required Experimental Test Parameters

PARAMETER	WSET	HHET
Air Pressure (P_a)	270 kPa	-
Air relative humidity (Rh)	-	>80%
Air temperature (T_a)	$-5.0^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$	$0.0^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$
Plate temperature (T_p)	$-5.0^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$	$-5.0^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$
Droplet size distribution	50% between 15 μm and 35 μm	-
Droplet volume average	20 $\mu\text{m} \pm 5 \mu\text{m}$	-
Icing intensity	5.0 g/dm ² /h $\pm$ 0.2 g/dm ² /h	0.30 g/dm ² /h $\pm$ 0.05 g/dm ² /h
Mean horizontal speed at 5 cm above test panel	-	0.2 m/s $\pm$ 0.1 m/s
Plate material	Al alloy 2024	Al alloy 2024
Roughness of the surface finish	$R_a \leq 0.5 \mu\text{m}$	$R_a \leq 0.5 \mu\text{m}$
Support temperature (T_p)	$-5.0^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$	$-5.0^{\circ}\text{C} \pm 0.5^{\circ}\text{C}$
Water conductivity	85 $\mu\text{Scm} \pm 5 \mu\text{Scm}$	85 $\mu\text{Scm} \pm 5 \mu\text{Scm}$
Water Flow Rate (WFR)	62 ml/min	-
Water pH level	6.8 $\pm$ 0.2	6.8 $\pm$ 0.2
Water pressure (P_w)	190 kPa	-




Figure 3 - Droplet Diameter Distribution in WSET

2.2 High Humidity Endurance Test

This test is designed to simulate the overnight exposure of an aircraft on the ground in open air with high relative humidity, the actual temperature of the aircraft being below the freezing point. During the HHET, a film of fluid, applied on a 10 cm x 30 cm aluminum plate, receives frost* at a prescribed deposition rate of $0.30 \text{ g/dm}^2/\text{h} \pm 0.05 \text{ g/dm}^2/\text{h}$. The plate presents a downward slope of 10° and is cooled to -5°C . To obtain the high level of water moisture required in HHET, humidity is generated by a 90 cm long, 60 cm wide and 30 cm deep water bath which is maintained at a temperature warmer than that of the air. Forced air circulates throughout the bath to increase surface area and promote evaporation of the water. The HHET set-up used in the present tests is shown in Figure 4. The experimental test parameters and other specifications are shown in Table 6. The air flow over the test plates is maintained at $0.2 \text{ m/s} \pm 0.1 \text{ m/s}$.

2.3 Measurements

The fluid viscosity is recorded with a Brookfield LVT viscometer, using the appropriate cylindrical spindle at 20°C (test method ASTM D2196) [5]. Fluid performance in a WSET or a HHET is evaluated from visual observations of the ice front position. These are done through a window by an observer outside the climatic chamber. Parameters measured during the test are as follows:

1. Anti-icing endurance time or **First Ice Event** (FIE) which corresponds to the period when the ice front first reaches the failure zone. The failure zone is defined as the area 25 mm below the upper edge of the test plate and 5 mm in from either side of the test plate (see Figure 2).
2. **Mean Icing Time** (MIT) which corresponds to the icing time needed to have an average 25 mm length of ice deposit on top of plate.

* FROST: type of ice formed by vapor deposition from high humidity air on a cold subzero (degree Celsius) surface.




Figure 4 - HHET Experimental Set-up

In order to provide FIE and MIT values corresponding to the required ice deposition rate, HHET and WSET are performed by subjecting the fluid to two test runs, where each test exposes a minimum of three plates with fluid and three plates without fluid (reference plates). Plate positions are reversed between test #1 and test #2. The individual ice mass received on each reference plate is used to check the rate of ice deposited on fluid-covered plates. This provides six anti-icing endurance time values to evaluate the fluid performance.

2.4 Calibration

By AMS 1424K [1] requirement, the icing rate during WSET is $5.0 \text{ g/dm}^2/\text{h} \pm 0.2 \text{ g/dm}^2/\text{h}$. The icing rate in HHET, as required by standard, has a value of $0.30 \text{ g/dm}^2/\text{h} \pm 0.05 \text{ g/dm}^2/\text{h}$. In order to provide several simultaneous measurements, the refrigerated support accommodates six plates $10 \text{ cm} \times 30 \text{ cm}$. The support consists of a refrigerated unit as shown in Figure 1. Preliminary work has shown that variations in ice weight around nominal values were observed from plate to plate. The variation in icing intensities as a function of the plate position are evaluated using calibration tests performed before standard tests. These calibration tests correspond to standard tests but without fluid. The mass of ice accumulated on each plate is measured after 120, 240 and 720 minutes, in the case of the HHET, and 30 min, in the case of WSET. In order to evaluate the distribution of the ice on the $10 \text{ cm} \times 30 \text{ cm}$ plates, eighteen smaller plates ($10 \text{ cm} \times 10 \text{ cm}$) are used to cover the entire support area. Figure 5 shows the position of the small plates on the refrigerated support.

1P1	2P1	3P1	4P1	5P1	6P1
1P2	2P2	3P2	4P2	5P2	6P2
1P3	2P3	3P3	4P3	5P3	6P3
P 1	P 2	P 3	P 4	P 5	P 6

Figure 5 - Small Plate Position on Support

3. TEST RESULTS

3.1 Test Presentation

Fluid sample identification is presented in Table 1 and the identification of the tests are presented in Table 2, while measured values of experimental parameters are presented in Table 6. In all standard tests, the fluids are at room temperature when applied to the plates, and the fluids were sheared within two hours of the beginning of the test. Air and plate temperatures are shown in the attachment at the end of the report. Viscosity results for the sheared dilutions are listed in Table 5.

Table 7 - Viscosity Measurement Details

Fluid Type	Measurement Device	Spindle #	Container Description	Sample Volume (ml)	Rotation Duration (min)		
					0.3 RPM	6 RPM	30 RPM
I	LV	1	600 ml Beaker	600	5	5	5
		2		600	5	5	5
		3		550	5	5	5
		4		550	5	5	5
II	SSA	31	13 R (P)	10	30	5	5
III		34	13 R (P)	10	30	5	5
IV		16	8 R (P)	4.2	30	5	5
		18	13 R (P)	8	30	5	5

The viscometers are calibrated yearly by the accredited laboratory CAN-AM Instruments Ltd. The NIST traceable calibration certificate is available upon request.

3.2 Calibration

Calibration tests, as defined in section 2.4, are performed before standard tests. The results are presented in Table 8. According to specifications [1], the system is considered adequately calibrated if the icing intensity is within the prescribed margin of $5.0 \text{ g/dm}^2/\text{h} \pm 0.2 \text{ g/dm}^2/\text{h}$ for WSET and $0.30 \text{ g/dm}^2/\text{h} \pm 0.05 \text{ g/dm}^2/\text{h}$ for HHET for each small plate. Accordingly, in WSET calibration data presented in Table 8 (WSC), all icing intensities are equal to $5.0 \text{ g/dm}^2/\text{h}$ within a range of $\pm 0.2 \text{ g/dm}^2/\text{h}$. In HHET calibration data presented in Table 8 (CAHH), all the icing intensities are equal to $0.30 \text{ g/dm}^2/\text{h}$ within a range of $\pm 0.05 \text{ g/dm}^2/\text{h}$.

Table 8 - Calibration Test Results

(g/dm ² /h)								
TEST	PLATE	P 1	P 2	P 3	P 4	P 5	P 6	OVERALL AVERAGE
WSC-2955 13-01-10 30 minutes	1	4.88	4.94	5.00	5.04	5.06	5.08	
	2	4.88	4.94	5.02	5.10	5.08	5.12	
	3	4.92	4.96	5.04	5.10	5.14	5.12	
	Average							5.02
CAHH-335 13-06-04 120 minutes	1	0.31	0.32	0.26	0.28	0.28	0.30	
	2	0.34	0.34	0.29	0.27	0.27	0.31	
	3	0.31	0.31	0.31	0.28	0.29	0.26	
	Average							0.30

3.3 Water Spray Endurance Test

FIE and MIT values as defined in section 2.3, are listed for each test run in Table 3, with identification of the plate positions and the mass of ice collected on the blank plates. Standard WSET is considered acceptable if the average icing intensity for each blank plate is equal to 5.0 g/dm²/h within a range of ± 0.2 g/dm²/h.

3.4 High Humidity Endurance Test

FIE and MIT values as defined in section 2.3 are shown for each standard test in Table 4, with identification of the plate positions and the weight of ice collected on adjacent blank plates. Standard HHET is considered acceptable if the average intensity for each blank plate is equal to 0.30 g/dm²/h within a range of ± 0.05 g/dm²/h.

4. REFERENCES

1. SAE International Aerospace Material Specification, "Deicing/Anti-icing Fluid, Aircraft, SAE Type I", AMS 1424, revision K, March 2012.
2. SAE International Aerospace Standard, "Water Spray and High Humidity Endurance Test Methods for SAE AMS 1424 and SAE AMS 1428 Aircraft Deicing/Anti-icing Fluids", AS5901, revision B, December 2010.
3. Laforte, J.-L., P. Louchez, G. Bouchard, and M. Farzaneh, "A Facility to Evaluate Performance of Aircraft Ground De/Anti-Icing Fluids Subjected to Freezing Rain". *Cold Regions Science and Technology*, 1990. **18**: p. 161-171.
4. Laforte, J.-L., P. Louchez, and G. Bouchard, "Cold and Humid Environment Simulation for De/Anti-Icing Fluids Evaluation". *Cold Regions Science and Technology*, 1992. **20**: p. 195-206.
5. American Society for Testing and Materials "Standard Test Methods for Rheological Properties of Non-Newtonian Materials by Rotational (Brookfield type) Viscometer", ASTM D 2196-10, 2010.

ATTACHMENT

TEST DATA SHEETS WITH AIR AND PLATE TEMPERATURE RECORDING

WSC-2955, p. 27

CAHH-335, p. 28

**DEICING FLUID ARCTON LTD.
Arctica DG91 Concentrate, lot # 11**

WSET	DILUTION 75/25	WS6732	p. 31
	DILUTION 75/25	WS6733	p. 32
	DILUTION 50/50	WS6730	p. 33
	DILUTION 50/50	WS6728	p. 34
HHET	DILUTION 75/25	HH3003	p. 35
	DILUTION 75/25	HH2988	p. 36
	DILUTION 50/50	HH2983	p. 37
	DILUTION 50/50	HH2972	p. 38

This page left blank.

TEST: WSC2955 DATE: 13-01-10 DURATION: 30 minutes

0mm						
25mm	I: 4.88 g/dm ² h	I: 4.94 g/dm ² h	I: 5.00 g/dm ² h	I: 5.04 g/dm ² h	I: 5.06 g/dm ² h	I: 5.08 g/dm ² h
100mm						
150mm	I: 4.88 g/dm ² h	I: 4.94 g/dm ² h	I: 5.02 g/dm ² h	I: 5.10 g/dm ² h	I: 5.08 g/dm ² h	I: 5.12 g/dm ² h
200mm						
300mm	I: 4.92 g/dm ² h	I: 4.96 g/dm ² h	I: 5.04 g/dm ² h	I: 5.10 g/dm ² h	I: 5.14 g/dm ² h	I: 5.12 g/dm ² h
	I _{av} : 4.89 σ: 0.02	I _{av} : 4.95 σ: 0.01	I _{av} : 5.02 σ: 0.02	I _{av} : 5.08 σ: 0.03	I _{av} : 5.09 σ: 0.04	I _{av} : 5.11 σ: 0.02
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -5.1±0.2°C T_p: -5.0±0.1°C Rh: 84.0±0.7% Ave. Icing Int.: 5.02±0.08g/dm²h

DELAY between shearing and test : n.a.

Comments:

TEST: CAHH335 DATE: 13-06-04 DURATION: 120 minutes

0mm						
25mm	I: 0.31 g/dm ² h	I: 0.32 g/dm ² h	I: 0.26 g/dm ² h	I: 0.28 g/dm ² h	I: 0.28 g/dm ² h	I: 0.30 g/dm ² h
100mm						
150mm	I: 0.34 g/dm ² h	I: 0.34 g/dm ² h	I: 0.29 g/dm ² h	I: 0.27 g/dm ² h	I: 0.27 g/dm ² h	I: 0.31 g/dm ² h
200mm						
300mm	I: 0.31 g/dm ² h	I: 0.31 g/dm ² h	I: 0.31 g/dm ² h	I: 0.28 g/dm ² h	I: 0.29 g/dm ² h	I: 0.26 g/dm ² h
	I _{av} : 0.32 σ: 0.02	I _{av} : 0.32 σ: 0.02	I _{av} : 0.29 σ: 0.03	I _{av} : 0.28 σ: 0.01	I _{av} : 0.28 σ: 0.01	I _{av} : 0.29 σ: 0.03
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -0.1±0.1°C T_p: -5.0±0.2°C Rh: 87.7±3.6% Ave. Icing Int: 0.30±0.02 g/dm²h


DELAY between shearing and test : n.a.

Comments:

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: WSC2955

DATE: 2013-01-10




Test length = 30 min

	Average	$\pm$	σ
T air	=	-5.1	$\pm$ 0.2
T plate	=	-5.0	$\pm$ 0.1
% Rh	=	84.0	$\pm$ 0.7

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: CAHH335

DATE: 2013-06-04



Test length = 121 min

	Average	$\pm$	σ
T air	=	-0.1	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.2
% Rh	=	87.7	$\pm$ 3.6

TEST: WS6732 DATE: 13-07-11 DURATION: 30 minutes

0mm						
25mm		FIE: 5min10s		FIE: 4min30s		FIE: 4min40s
	I: 4.88 g/dm ² h	MIT: 6min10s	I: 4.82 g/dm ² h	MIT: 6min00s	I: 4.82 g/dm ² h	MIT: 6min20s
100mm						
150mm	I: 4.96 g/dm ² h	fluid : J160	I: 5.02 g/dm ² h	fluid : J160	I: 4.98 g/dm ² h	fluid : J160
200mm		75/25 Arctica DG91		75/25 Arctica DG91		75/25 Arctica DG91
		Concentrate Lot # 11		Concentrate Lot # 11		Concentrate Lot # 11
300mm	I: 5.06 g/dm ² h		I: 5.08 g/dm ² h		I: 5.04 g/dm ² h	
	I _{av} : 4.97 σ: 0.09		I _{av} : 4.97 σ: 0.14		I _{av} : 4.95 σ: 0.11	
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -4.9±0.1°C T_p: -5.0±0.1°C Rh: 77.5±2.2% Ave. Icing Int.: 4.96±0.10g/dm²h

DELAY between shearing and test : 67 minutes.

Comments:

TEST: WS6733

DATE: 13-07-12

DURATION: 30 minutes

0mm						
25mm	FIE: 4min30s		FIE: 4min40s		FIE: 4min55s	
	MIT: 6min15s	I: 4.82 g/dm ² h	MIT: 6min05s	I: 4.86 g/dm ² h	MIT: 6min10s	I: 4.82 g/dm ² h
100mm						
150mm	fluid : J160	I: 4.88 g/dm ² h	fluid : J160	I: 5.00 g/dm ² h	fluid : J160	I: 4.96 g/dm ² h
200mm	75/25 Arctica DG91		75/25 Arctica DG91		75/25 Arctica DG91	
	Concentrate Lot # 11	I: 4.90 g/dm ² h	Concentrate Lot # 11	I: 4.98 g/dm ² h	Concentrate Lot # 11	I: 4.86 g/dm ² h
300mm						
	I _{av} : 4.87 σ: 0.04		I _{av} : 4.95 σ: 0.08		I _{av} : 4.88 σ: 0.07	
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -5.0±0.1°C T_p: -5.0±0.0°C Rh: 83.5±1.2% Ave. Icing Int.: 4.90±0.07g/dm²h

DELAY between shearing and test : 35 minutes.

Comments:

TEST: WS6730

DATE: 13-07-10

DURATION: 30 minutes

0mm					
25mm		FIE: 3min00s		FIE: 3min00s	FIE: 3min05s
	I: 5.00 g/dm ² h	MIT: 3min30s	I: 4.84 g/dm ² h	MIT: 3min20s	MIT: 3min25s
100mm					
150mm	I: 5.00 g/dm ² h	fluid : J161	I: 4.92 g/dm ² h	fluid : J161	fluid : J161
200mm		50/50 Arctica DG91		50/50 Arctica DG91	50/50 Arctica DG91
	I: 5.10 g/dm ² h	Concentrate Lot # 11	I: 4.96 g/dm ² h	Concentrate Lot # 11	Concentrate Lot # 11
300mm					
	I _{av} : 5.03 σ: 0.06		I _{av} : 4.91 σ: 0.06		I _{av} : 4.92 σ: 0.11
	P1	P2	P3	P4	P5
					P6

n.m. not measured
n.a. not applicable

T_a: -5.0±0.1°C T_p: -5.0±0.1°C Rh: 76.2±3.7% Ave. Icing Int.: 4.95±0.09g/dm²h

DELAY between shearing and test : 61 minutes.

Comments:

TEST: WS6728

DATE: 13-07-09

DURATION: 30 minutes

0mm						
25mm	FIE: 3min20s		FIE: 3min30s		FIE: 3min30s	
	MIT: 3min40s	I: 4.86 g/dm ² h	MIT: 3min55s	I: 4.84 g/dm ² h	MIT: 4min00s	I: 4.82 g/dm ² h
100mm						
150mm	fluid : J161	I: 4.90 g/dm ² h	fluid : J161	I: 4.92 g/dm ² h	fluid : J161	I: 4.94 g/dm ² h
200mm	50/50 Arctica DG91		50/50 Arctica DG91		50/50 Arctica DG91	
	Concentrate Lot # 11	I: 4.94 g/dm ² h	Concentrate Lot # 11	I: 4.96 g/dm ² h	Concentrate Lot # 11	I: 4.92 g/dm ² h
300mm						
		I _{av} : 4.90 σ: 0.04		I _{av} : 4.91 σ: 0.06		I _{av} : 4.89 σ: 0.06
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -5.0±0.1°C T_p: -5.0±0.1°C Rh: 76.3±3.1% Ave. Icing Int.: 4.90±0.05g/dm²h

DELAY between shearing and test : 62 minutes.

Comments:

TEST: HH3003

DATE: 13-07-26

DURATION: 120 minutes

0mm					
25mm		FIE: 26min45s		FIE: 30min40s	FIE: 31min20s
	I: 0.34 g/dm ² h	MIT: 28min00s	I: 0.31 g/dm ² h	MIT: 32min30s	MIT: 33min45s
100mm					
150mm	I: 0.34 g/dm ² h	fluid : J160	I: 0.31 g/dm ² h	fluid : J160	fluid : J160
200mm		75/25 Arctica DG91		75/25 Arctica DG91	75/25 Arctica DG91
		Concentrate Lot # 11		Concentrate Lot # 11	Concentrate Lot # 11
300mm	I: 0.29 g/dm ² h		I: 0.27 g/dm ² h	I: 0.31 g/dm ² h	
	I _{av} : 0.32 σ: 0.03		I _{av} : 0.30 σ: 0.02		I _{av} : 0.31 σ: 0.01
	P1	P2	P3	P4	P5
					P6

n.m. not measured
n.a. not applicable

T_a: -0.1±0.1°C T_p: -5.0±0.0°C Rh: 91.9±1.3% Ave. Icing Int.: 0.31±0.02 g/dm²h

DELAY between shearing and test : 23 minutes.

Comments:

TEST: HH2988

DATE: 13-07-11

DURATION: 120 minutes

0mm						
25mm	FIE: 27min45s		FIE: 28min10s		FIE: 31min10s	
	MIT: 34min30s	I: 0.31 g/dm ² h	MIT: 32min25s	I: 0.31 g/dm ² h	MIT: 35min00s	I: 0.32 g/dm ² h
100mm						
150mm	fluid : J160	I: 0.31 g/dm ² h	fluid : J160	I: 0.30 g/dm ² h	fluid : J160	I: 0.34 g/dm ² h
200mm	75/25 Arctica DG91		75/25 Arctica DG91		75/25 Arctica DG91	
	Concentrate Lot # 11	I: 0.31 g/dm ² h	Concentrate Lot # 11	I: 0.30 g/dm ² h	Concentrate Lot # 11	I: 0.28 g/dm ² h
300mm						
		I _{av} : 0.31 σ: 0.00		I _{av} : 0.30 σ: 0.01		I _{av} : 0.31 σ: 0.03
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -0.1±0.1°C T_p: -5.0±0.1°C Rh: 927±15% Ave. Icing Int.: 0.31±0.02g/dm²h

DELAY between shearing and test : 25 minutes.

Comments:

TEST: HH2983

DATE: 13-07-05

DURATION: 120 minutes

0mm					
25mm	I: 0.33 g/dm ² h	FIE: 21min05s MIT: 22min10s	I: 0.29 g/dm ² h	FIE: 21min05s MIT: 22min20s	I: 0.31 g/dm ² h FIE: 22min40s MIT: 23min20s
100mm					
150mm	I: 0.35 g/dm ² h	fluid : J161	I: 0.30 g/dm ² h	fluid : J161	fluid : J161
200mm		50/50 Arctica DG91		50/50 Arctica DG91	50/50 Arctica DG91
300mm	I: 0.31g/dm ² h	Concentrate Lot # 11	I: 0.29 g/dm ² h	Concentrate Lot # 11	Concentrate Lot # 11
	I _{av} : 0.33 σ: 0.02		I _{av} : 0.29 σ: 0.01		I _{av} : 0.31 σ: 0.02
	P1	P2	P3	P4	P6

n.m. not measured
n.a. not applicable

T_a: -0.1±0.1°C T_p: -5.0±0.0°C Rh: 92.2±1.6% Ave. Icing Int.: 0.31±0.02g/dm²h

DELAY between shearing and test : 61 minutes.

Comments:

TEST: HH2972

DATE: 13-06-17

DURATION: 120 minutes

0mm						
25mm	FIE: 23min40s		FIE: 25min20s		FIE: 26min10s	
	MIT: 25min30s	I: 0.31 g/dm ² h	MIT: 27min30s	I: 0.28 g/dm ² h	MIT: 28min10s	I: 0.28 g/dm ² h
100mm						
150mm	fluid : J161	I: 0.31 g/dm ² h	fluid : J161	I: 0.27 g/dm ² h	fluid : J161	I: 0.30 g/dm ² h
200mm	50/50 Arctica DG91		50/50 Arctica DG91		50/50 Arctica DG91	
	Concentrate Lot # 11	I: 0.29 g/dm ² h	Concentrate Lot # 11	I: 0.27 g/dm ² h	Concentrate Lot # 11	I: 0.26 g/dm ² h
300mm						
		I _{av} : 0.30 σ: 0.01		I _{av} : 0.27 σ: 0.01		I _{av} : 0.28 σ: 0.02
	P1	P2	P3	P4	P5	P6

n.m. not measured
n.a. not applicable

T_a: -0.1±0.1°C T_p: -5.0±0.0°C Rh: 87.8±2.4% Ave. Icing Int.: 0.29±0.02g/dm²h


DELAY between shearing and test : 58 minutes.

Comments:

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: WS6732

DATE: 2013-07-11




Test length = 30 min

	Average	$\pm$	σ
T air	=	-4.9	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.1
% Rh	=	77.5	$\pm$ 2.2

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: WS6733

DATE: 2013-07-12




Test length = 30 min

	Average	$\pm$	σ
T air	=	-5.0	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.0
% Rh	=	83.5	$\pm$ 1.2

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: WS6730

DATE: 2013-07-10




Test length = 30 min

	Average	$\pm$	σ
T air	=	-5.0	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.1
% Rh	=	76.2	$\pm$ 3.7

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: WS6728

DATE: 2013-07-09




Test length = 30 min

	Average	$\pm$	σ
T air	=	-5.0	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.1
% Rh	=	76.3	$\pm$ 3.1

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: HH3003

DATE: 2013-07-26




Test length = 120 min

	Average	$\pm$	σ
T air	=	-0.1	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.0
% Rh	=	91.9	$\pm$ 1.3

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: HH2988

DATE: 2013-07-11




Test length = 361 min

	Average	$\pm$	σ
T air	=	-0.1	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.1
% Rh	=	92.7	$\pm$ 1.5

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: HH2983

DATE: 2013-07-05




Test length = 120 min

	Average	±	σ
T air	=	-0.1	± 0.1
T plate	=	-5.0	± 0.0
% Rh	=	92.2	± 1.6

RELATIVE HUMIDITY, AIR AND PLATE TEMPERATURES

TEST: HH2972

DATE: 2013-06-17



Test length = 120 min

	Average	$\pm$	σ
T air	=	-0.1	$\pm$ 0.1
T plate	=	-5.0	$\pm$ 0.0
% Rh	=	87.8	$\pm$ 2.4